

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁴ : A61F 2/54	A1	(11) International Publication Number: WO 88/ 02623 (43) International Publication Date: 21 April 1988 (21.04.88)
(21) International Application Number: PCT/US87/02675 (22) International Filing Date: 16 October 1987 (16.10.87) (31) Priority Application Number: 920,567 (32) Priority Date: 17 October 1986 (17.10.86) (33) Priority Country: US (71) Applicant: BIO-METRIC SYSTEMS, INC. [US/US]; 9932 West 74th Street, Eden Prairie, MN 55344 (US). (72) Inventor: GUIRE, Patrick, E. ; 6741 Tartan Curve, Eden Prairie, MN 55344 (US). (74) Agents: BAUMAN, Mary, P. et al.; Fredrikson & Byron, 1100 International Centre, 900 2nd Avenue South, Minneapolis, MN 55402-3397 (US).		(81) Designated States: AT (European patent), AU, BE (European patent), CH (European patent), DE (European patent), DK, FR (European patent), GB (European patent), IT (European patent), JP, LU (European patent), NL (European patent), NO, SE (European patent). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

(54) Title: IMPROVEMENT OF THE BIOCOMPATIBILITY OF SOLID SURFACES**(57) Abstract**

The biocompatibility of biomaterials having solid surfaces is improved through coating the same with biocompatible agents. The method for modifying the solid surface to improve biocompatibility employs molecules of a biocompatible agent and a chemical linking moiety possessing a photochemically reactive group capable upon activation of covalently bonding to the solid surface and possessing a different reactive group as capable upon activation of covalently bonding to separate molecules of the biocompatible agent. One of the groups is unresponsive to activation by a stimulus to which the other group is responsive. The method comprises applying stimulus to sequentially activate the groups and covalently bind the different reactive group of the linking moiety to the molecules of the biocompatible agent and to photochemically covalently bind the linking moiety to the solid surface with a sufficient population density to enable the molecules of the biocompatible agent to effectively shield the solid surface and to provide a biocompatible surface.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	ML	Mali
AU	Australia	GA	Gabon	MR	Mauritania
BB	Barbados	GB	United Kingdom	MW	Malawi
BE	Belgium	HU	Hungary	NL	Netherlands
BG	Bulgaria	IT	Italy	NO	Norway
BJ	Benin	JP	Japan	RO	Romania
BR	Brazil	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	LI	Liechtenstein	SN	Senegal
CH	Switzerland	LK	Sri Lanka	SU	Soviet Union
CM	Cameroon	LU	Luxembourg	TD	Chad
DE	Germany, Federal Republic of	MC	Monaco	TG	Togo
DK	Denmark	MG	Madagascar	US	United States of America
FI	Finland				

1

IMPROVEMENT OF THE BIOCOMPATIBILITY
OF SOLID SURFACES

FIELD OF INVENTION

This invention relates to the field of bio-chemistry and particularly to the enhancement of the biocompatibility of various surfaces.

BACKGROUND OF THE INVENTION

The implantation of such biomaterial articles as substitute blood vessels, synthetic and intraocular lenses, electrodes, catheters and the like in and onto the body is a rapidly developing area of medicine. A primary impediment to the long-term use of such biomaterial implantables as synthetic vascular grafts has been the lack of satisfactory graft surfaces. The uncoated surfaces of synthetic blood vessels made from plastics, for example, often stimulate rapid thrombogenic action. Various plasma proteins play a role in initiating platelet and fibrin deposition on plastic surfaces. These actions lead to vascular constriction to hinder blood flow, and the inflammatory reaction that follows can lead to the loss of function of the synthetic implantable.

A "biomaterial" may be defined as a material that is substantially insoluble in body fluids and that is designed and constructed to be placed in or onto the body or to contact fluid of the body. Vascular grafts and contact lenses are examples of biomaterials.

Ideally, a biomaterial will have the following characteristics:

1. It will not induce undesirable reactions in the body such as blood clotting, tissue death, tumor formation, allergic reaction, foreign body reaction (rejection) or inflammatory reaction.
2. It will have the physical properties such as strength, elasticity, permeability and flexibility required to function as intended.
3. It can be purified, fabricated and sterilized easily.
4. It will substantially maintain its physical properties and function during the time that it remains implanted in or in contact with the body, whether it be an hour or a lifetime.

As used herein, the solid surface of a biomaterial is characterized as "biocompatible" if it is capable of functioning or existing in contact with biological fluid and/or tissue of a living organism with a net beneficial effect on the living organism. Long term biocompatibility is desired for the purpose of reducing disturbance of the host organism.

A number of approaches have been suggested to improve the biocompatibility of implantable items. One approach has been to modify the surface of a biomaterial to prevent undesirable protein adhesion by providing the biomaterial with a low polarity surface, a negatively charged surface or a surface coated with biological materials such as enzymes, endothelial

cells and proteins. Solid surfaces have been coated with biochemical materials such as heparin, albumin and streptokinase to enhance thromboresistance. Albumin in particular has been physically adsorbed onto and electrostatically and covalently bound to polymer surfaces.

Munro, et. al, U.S. Patent No. 4,530,974 discloses a method of adsorbing albumin to a water-insoluble polymer such as polyurethane by covalently binding to the surface a nonionic hydrophobic aliphatic chain to which albumin will selectively bind.

Nimni et al, U.S. Patent 4,378,224 teaches a method of coating animal tissues, used to make prosthetic devices, through the formation of a three dimensional cross-linked matrix primarily composed of a calcification inhibitor.

An example of an adverse reaction that is caused by the presence of a biomaterial is the deposition of protein on contact lenses. Often contact lens wearers develop an intolerance to their contact lenses with time and this intolerance may be linked to irritation and allergic responses to biochemicals (proteins, lipids, mucopolysaccharides, and others) which deposit onto the lenses while they are worn. Current cleansing and disinfection procedures remove some of these deposits, but these procedures often leave holes and crevices in the lenses which add to the eye irritation of the wearer and serve as foci for further biochemical deposition.

Guire, U.S. Patent No. 3,959,078, describes the use of reagents to covalently bind an enzyme to aminoethyl cellulose or alkylamine glass. See, also: Guire, Stepwise Thermophotochemical Cross-linking for

Enzyme Stabilization and Immobilization; Enzyme Engineering 3:63-70 (1978) and Guire, Photochemical Immobilization of Enzymes and Other Biochemicals, Methods in Enzymology XLIV:280-288 (1976). These references describe a process of covalently binding an enzyme to substrates such as chemical derivatives of controlled-pore glass, cellulose, agarose and polyacrylamides by thermochemically coupling a linking reagent to the solid surface and photochemically coupling the enzyme to the linking reagent to provide a surface useful in the performance of in vitro diagnostic assays.

SUMMARY OF THE INVENTION

The invention relates to biomaterials that are provided with desired biocompatible surfaces. A method for modifying the solid surface of a biomaterial employs molecules of a biocompatible agent and a chemical-linking moiety possessing a photochemically reactive group capable, upon activation, of covalently bonding to the solid surface and possessing a different reactive group that is capable, upon activation, of covalently bonding to separate molecules of the biocompatible agent. One of the groups is unresponsive to activation by a stimulus to which the other group is responsive. The method comprises applying stimulus to sequentially activate the groups to covalently bind the different reactive group of the linking moiety to the molecules of the biocompatible agent and to photochemically covalently bind the linking moiety to the solid surface with a sufficient population density to enable the molecules of the biocompatible agent to effectively shield the solid surface and to provide a biocompatible effective surface.

A biocompatible "effective" surface is thus formed of a plurality of separate molecules of a biocompatible agent covalently linked, through a linking

moiety, to the solid surface of a biomaterial to provide that surface with substantially the same biocompatible characteristics as are possessed by the biocompatible agent. The effective surface formed by the molecules of the biocompatible agent need not cover the entire surface of a biomaterial. It may cover the surface in spots. For example, spots along the surface of vascular grafts may be covered by a cell attachment factor such as fibronectin. The biocompatible effective surface formed at those spots then act as foci for attachment of cells to the modified surface.

The different reactive group of the linking moiety desirably is a thermochemical group or a photochemical group that is unresponsive to the stimulus to which the first mentioned photochemically reactive group responds and to which molecules of the biocompatible agent will covalently bind.

In another embodiment of the invention there is provided a device having a biocompatible effective surface formed of separate molecules of a biocompatible agent covalently linked by a chemical linking moiety residue to the solid surface of the device. The chemical linking moiety residue includes a residue of a photochemically reactive group covalently bonded to the solid surface, and, covalently bonded to molecules of the biocompatible agent, the residue of a different reactive group, one of the reactive groups being unresponsive to a stimulus to which the other reactive group responds. The individual molecules of the biocompatible agent are attached through the linking moiety residue to the solid surface sufficiently proximate to one another as to cause said molecules to effectively shield the solid surface and to provide a biocompatible effective surface.

The biocompatible agent is chosen to enhance the function of a particular device. For example, the function of contact lenses may be enhanced by attaching molecules of polyethylene glycol to the lens surfaces to diminish the deposition of proteins on these surfaces. As another example, a cell attachment factor such as fibronectin or laminin may be bonded to a device having a polyvinyl chloride surface to increase cell attachment to the device. This is desirable in the case of implantables such as catheters and substitute blood vessels.

Yet another embodiment of the invention involves a method for modifying the solid surface of a biomaterial, the method employing molecules of a biocompatible agent joined to one another to form a biocompatible film, and a chemical linking moiety capable of linking the film to the solid surface of the biomaterial. The chemical linking moiety includes a, photochemically reactive group capable upon activation of covalently bonding to the solid surface, and the residue of a reactive group covalently bonded to the film (e.g., to the residue of the biocompatible agent molecules making up the film). One of the reactive groups is unresponsive to a stimulus to which the other reactive group responds. The method comprises activating the photochemically reactive group with a stimulus to covalently bind the biocompatible molecules. By "joined" in this context, reference is made not only to covalent bonding of adjacent biocompatible agent molecules but also to interactions caused by such forces as hydrogen bonding, ionic bonding, bonding through Van der Waals forces, and the like.

The biocompatible agent having molecules joined to one another to form a film may comprise molecules of one agent or it may comprise molecules of two or more agents such as heparin and albumin.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The solid surface that is rendered biocompatible in accordance with the invention desirably is of a synthetic or natural material that is insoluble in physiological fluids. The surface may be one or more surfaces of devices intended to function in contact with tissue and/or fluids of living organisms. The solid surface of the device may be any suitable metal such as polished titanium or stainless steel or a polymer such as polyurethane, polyvinylpyrrolidone, silicone elastomers, polyethylene, polytetrafluoroethylene, poly-(p-phenyleneterephthalamide), polyvinyl chloride, polypropylene, polyolefins, polyesters, polyacrylates (including polymethacrylates); minerals or ceramics such as hydroxyapatite; human tissue such as bone, skin and teeth; organic materials such as wood, cellulose and compressed carbon; and other natural and synthetic materials such as glass, rubber, wood and the like. Examples of devices which may be provided with biocompatible surfaces in accordance with this invention include vascular graft tubing, dialysis tubing or membrane, blood oxygenator tubing or membrane, ultrafiltration membrane, intra-aortic balloon, blood bag, catheter, suture, soft or hard tissue prosthesis, synthetic prosthesis, artificial organs, and lenses for the eye such as contact and intraocular lenses.

The solid surface is desirably thermochemically unreactive. "Thermochemically unreactive" means that the surface is free of any surface treatment designed to increase the ability of the surface to thermochemically react. Examples of thermochemically unreactive surfaces include polytetrafluoroethylene, polyethylene, polypropylene, polyvinyl chloride, polyvinylpyrrolidone, silicone elastomers, stainless steel and titanium.

Molecules of a biocompatible agent are attached to the surfaces of biomaterials to improve biocompatibility. The biocompatible agent may be a growth factor such as endothelial cell growth factor, epithelial cell growth factor, osteoblast growth factor, fibroblast growth factor, platelet derived growth factor, neural growth factor, or angiogenin growth factor; an antimicrobial agent such as lysosyme or penicillin; an antithrombogenic agent such as heparin, albumin, streptokinase, tissue plasminogen activator (TPA) or urokinase; a thrombogenic agent such as collagen or a hydrophilic polymer such as polyethylene glycol, hyluronic acid, chitosan or methyl cellulose, and other proteins, carbohydrates and fatty acids. The biocompatible agent may comprise molecules of one of the above listed agents or it may comprise molecules of two or more agents. For example, the biocompatible agent may comprise molecules of both albumin and heparin.

In one embodiment the molecules of a biocompatible material are joined to one another to form a film that is attached to a solid surface by a linking moiety. The biocompatible agent desirably may be hyaluronic acid or albumin. A biocompatible device having a film attached may be an artificial hip joint coated with a film of hyaluronic acid.

The chemical linking moiety preferably has the formula A-X-B in which A represents a photochemically reactive group capable in response to specific activation of bonding covalently to a solid surface; B represents a different reactive group capable desirably in response to specific activation to which group A is unresponsive, of forming a covalent bond to a biocompatible agent and X represents a relatively inert, noninterfering skeletal moiety joining groups "A", and

- 9 -

"B", that is resistant to cleavage in aqueous physiological fluid. The physiological fluid referred to is such fluid with which X will come in contact.

X is preferably a C_1 - C_{10} alkyl group such as polymethylene, a carbohydrate such as polymethylol, a polyoxyethylene, such as polyethylene glycol or a polypeptide such as polylysine.

The reactive group B is a group that upon suitable activation covalently bonds to proteinaceous or other biocompatible agents. Such groups are typified by thermochemical groups and photochemical groups, as described and exemplified in Guire, U.S. Patent 3,959,078, the teachings of which are incorporated herein by reference.

The photochemically reactive groups (A) (the covalent bonding of which is activated by actinic radiation) may be typified by aryl, alkyl and acyl azides, oxazidines, isocyanates (nitrene generators), alkyl and 2-ketodiazole derivatives and diazirines (carbene generators), aromatic ketones (triplet oxygen generators), aromatic diazonium derivatives and numerous classes of carbonium ion and radical generators. Reference is made to Frederick J. Darfler and Andrew M. Tometsko, chapter 2 of Chemistry and Biochemistry of Amino Acids, Peptides and Proteins (Boris Weinstein, ed) vol. 5, Marcel Dekker, Inc. New York, 1978, for further description of photochemically reactive groups. Azidonitrophenyls, fluoroazido nitrobenzenes, and aromatic ketones form a preferred group due to their stability to chemical reaction conditions in the dark and their susceptibility to activation by light of wave lengths harmless to most biomaterials, to form short-lived reactive

intermediates capable of forming covalent bonds in useful yield with most sites on the biomaterial.

Nitrophenylazide derivatives (shown as including the - X - group) appropriate for use as photochemically reactive groups for the most part can be derived from fluoro-2-nitro-4-azidobenzene, and include 4-azido-2-nitrophenyl(ANP)-4-amino-butyryl, ANP-6-aminocaproyl, ANP-11-aminoundecanoyl, ANP-glycyl, ANP-aminopropyl, ANP-mercaptoethylamino, ANP-diaminohexyl, ANP-diaminopropyl, and ANP-polyethylene glycol. ANP-6-aminocaproyl, ANP-11-aminoundecanoyl, and ANP-polyethylene glycol are preferred. Aromatic ketones preferred for use as photochemically reactive groups include benzylbenzoyl and nitrobenzylbenzoyl.

Thermochemical reactive groups (that are activated by heat energy) are typified by and include nitrophenylhalides, alkylamino, alkylcarboxyl, alkylthiol, alkylaldehyde, alkylmethylimidate, alkylisocyanate, alkylisothiocyanate and alkylhalide groups.

Groups appropriate for use as thermochemically reactive groups include carboxyl groups, hydroxyl groups, primary amino groups, thiol groups, maleimides and halide groups. N-oxysuccinimide carboxylic esters of such groups as 6-amino hexanoic acid and amino undecanoic acid, alkylthiol groups such as mercaptosuccinic anhydride and beta-mercaptopropionic acid, homocysteinethiolactones, and polyethylene glycol derivatives are preferred.

The devices of this invention have biocompatible solid surfaces that include molecules of a biocompatible agent and a chemical linking moiety residue. The chemical linking moiety residue possesses a

- 11 -

residue of a photochemically reactive group bonded to the solid surface and possesses a residue of a different reactive group covalently bonded to the biocompatible agent. The residue of the photochemically reactive group is that portion of a photoreactive group (described above) represented by "A" in the general formula, that remains after a covalent bond has formed. When the photoreactive group is ANP and the solid substrate is polyethylene, the residue is a carbon-nitrogen bond. A nitrene formed when ANP is light-activated, reacts with a carbon of the polyethylene to form a covalent bond. When the photoreactive group is BBA and the solid substrate is polyethylene, the residue is a carbon-carbon bond. When BBA is stimulated by light, the carbon joining the two phenyl groups is activated to a triplet state causing a carbon-carbon bond to form between the polyethylene and the BBA and to form an hydroxyl group. When the different reactive group ("B") is NOS the residue is the carboxyl carbon of that group bonded to an oxygen or nitrogen group of a biocompatible agent such as fibronectin.

As enzymes, cell attachment factors and certain other substances that may be employed as biocompatible agents are somewhat sensitive to high temperatures, it is desired that the different reactive group on the linking moiety employed in the present invention be activated by (that is, undergo covalent bonding in response to) easily applied and nonharmful stimuli such as moderate heat (e.g., body temperature or below) and light. Reactive groups that are unresponsive to the stimulus to which the photochemically reactive

group responds may be groups that react to changes in pH, or to the addition of another chemical species and the like.

The chemical linking moieties desirably covalently bond to the surface in such population to enable the molecules of biocompatible agent moieties to shield the solid surface and to provide a biocompatible effective surface. The density of bound chemical moieties necessary to provide an effective surface varies with the particular biocompatible agent used.

The invention may be better understood by reference to the following non-limiting examples. Table 1 is a list of abbreviations of terms used in the following descriptions.

TABLE 1: LIST OF ABBREVIATIONS

<u>Abbreviation</u>	<u>Full Name</u>
EGF	Endothelial growth factor
PEG	Polyethylene glycol
PVC	Polyvinyl chloride
PE	Polyethylene
PP	Polypropylene
PTFE	Polytetrafluoroethylene
FNAB	Fluoronitroazidobenzene
ANP	4-azido-2-nitrophenyl
KOH	Potassium hydroxide
TLC	Thin layer chromatography
NOS	N-oxysuccinimide
EAC(A)	Epsilon amino caproic acid
AUD(A)	Amino undecanoic acid
BBA	Benzoyl benzoic acid
DMSO	Dimethyl sulfoxide
DMF	Dimethylformamide
EDC	1-ethyl-3-(3-dimethylamino-propyl) carbodimide
PEG-1000	Polyethylene glycol, molecular weight 1000
PEG-4000	Polyethylene glycol molecular weight 4000
PBS	Phosphate buffered saline
FN	Fibronectin
COL	Collagen
nBBA	Nitrobenzoylbenzoic acid
HEPES	N-2-hydroxyethylpiperazine - N'-2-ethane sulfonic acid
HSA	Human serum albumin
HGG	Human gamma globulin
LYZ	Lyzosyme
mmole	millimole

TABLE 1 Continued: LIST OF ABBREVIATIONS

<u>Abbreviation</u>	<u>Full Name</u>
ml	milliliter
MW _{app}	Approximate molecular weight
mg	milligram
M	Molar
pmole	picamole
ng	nanogram
ug	microgram
ID	Inner diameter

Example 1Endothelial Cell Attachment/Growth

1. Plastic Surfaces. Various cell factors were coupled to polymeric surfaces tested in vitro to determine the effect of these factors upon cell attachment and overgrowth. The polymeric surfaces included polyvinyl chloride (PVC), polyethylene (PE), polypropylene (PP) and polytetrafluoroethylene (PTFE) GORE-TEX (6mm reinforced expanded PTFE, a trademarked product of W. L. Gore and Associates, Inc.). Commercial tubing tested included polyester (Dacron, D, 6mm straight knitted dacron velour, a trademarked product of Dupont), silicone elastomer, (Silastic^R, S, 0.03 I.D., tubing, a trademarked product of Dow Corning) and polyurethane. Polystyrene plates were used as controls.

2. Preparation of the Chemical Linking Moiety. The chemical linking moiety used in these examples were the N-oxy succinimide (NOS) esters of 4-azido-2-nitrophenyl epsilon amino caproic acid (ANP-EACA), 4-azido-2-nitro-phenyl amino undecanoic acid (ANP-AUDA) and benzoylbenzoic acid (BBA).

ANP-EAC-NOS and ANP-AUD-NOS were prepared by the method described in P. Guire, D. Fliger and J. Hodgson, "Photochemical Coupling of Enzymes to Mammalian Cells", Pharmacological Research Communications, Vol. 9, pp 131-141 (1977), incorporated herein by reference. Briefly, fluoro-2-nitro-4-azido benzene was reacted with either epsilon amino caproic acid or amino undecanoic acid to substitute the relatively poorly reactive fluoride with an amino alkyl carboxy group. The carboxy group was then esterified, by carbodiimide activation with N-hydroxy succinimide to yield the N-oxy succinimide carboxylic ester. The NOS ester of benzoylbenzoic acid was prepared by esterifying the carboxy group by carbodiimide activation with N-hydroxy succinimide.

When ANP-EAC-NOS or ANP-AUD-NOS is the chemical linking moiety used, the ANP group is the photochemically reactive group, represented by the letter "A" in the A-X-B general formula discussed above. The NOS group is the different reactive group represented by the letter "B" in the formula. The EAC or AUD group acts as the spacer between the two reactive groups and is represented by the X in the general formula. When BBA-NOS is the chemical linking moiety, the benzoylbenzoic group is the photochemically reactive group represented by the "A" in the general formula and the NOS group is the different reactive group represented by the letter "B". The group represented by X is the carbon connecting the two reactive groups.

3. Covalent Bonding of Growth Factors to the Chemical Linking Moieties. The biocompatible agents fibronectin, laminin, collagen, endothelial growth

- 16 -

factor, and human serum albumin were tested for their abilities to promote endothelial cell attachment and overgrowth on synthetic biomaterials. These agents were coupled to the N-oxysuccinimide (NOS) esters of 4-azido-2-nitrophenyl epsilon amino caproic acid (ANP-EACA), 4-azido-2-nitrophenyl-undecanoic amino acid (ANP-AUDA) or benzoylbenzoic acid (BBA) as follows. As used herein "photolabeled" refers to a biocompatible agent that has been coupled to a chemical linking moiety by the different reactive group and that has a photochemically reactive group.

A. Covalent Binding of Fibronectin and Laminin to the Linking Moiety. Human fibronectin (University of Wisconsin Medical School) and mouse laminin (obtained from Bethesda Research Lab.) were separately dissolved at 1 mg/ml concentrations in 0.1M borate, pH 9.0. A solution of ANP-EAC-NOS in dry dimethylformamide ("DMF"), ANP-AUD-NOS in dry DMF, or BBA-NOS in dry dioxane was slowly added to the fibronectin or laminin solution in equimolar amounts to the concentration of protein epsilon amino groups (lysine residues) by syringe drive at 4°C in the dark over 16 hours. Then the mixture was stirred 4 hours in the cold. The fibronectin or laminin solution was centrifuged to remove insoluble material then applied to a Sephadex G-75 column to remove uncoupled photoreagent. The fractions were monitored at 260nm and 462nm to assess the photogroup/protein ratios.

B. Covalent Binding of EGF, Collagen, and HSA to Chemical Linking Moieties. Human placenta Type IV collagen (Sigma Pharmaceutical), endothelial growth factor (Sigma Pharmaceutical), and human serum albumin (Sigma Pharmaceutical) were separately dissolved at 2 mg/ml concentrations in 0.1M borate, pH 9.0. solution of ANP-EAC-NOS in DMF, ANP-AUD-NOS in

DMF or BBA-NOS in dioxane was slowly added to the solution containing the biocompatible agent in 5X molar amounts to the concentration of epsilon amino groups (lysine) residues by syringe drive at 4°C in the dark over 16 hours. Then the solution was dialyzed against 4 1000ml changes of phosphate buffered saline (PBS) and centrifuged to remove insoluble material. The product was analyzed at 260nm, 280nm and 462nm to assess the photogroup/protein ratios.

4. Covalently Binding the Biocompatible Agents to Plastic Surfaces. Various sheets, tubes and flat pieces of polyethylene, polyvinyl chloride, polypropylene, polyurethane, Dacron^R (velour), Silastic^R (medical grade), and polytetrafluoroethylene above were used. A 0.05ml aliquot of solutions containing 0 to 500 ug/ml of photolabeled biocompatible agent was added to each 0.5 cm² section of plastic surface. The solution was allowed to adsorb onto each piece for 3 hours at room temperature in the dark. The excess liquid was removed and the biocompatible agents were covalently linked to the surfaces by photolysis for 12 hours at the appropriate wavelength (Tungsten "spotlite" for ANP and long wavelength UV for BBA). After photolysis, the specimens were washed with a 4 second stream of PBS to remove non-covalently linked molecules of photolabeled biocompatible agent. The pieces were then placed in tissue culture to assess the endothelial cell reaction to the cell factors as follows.

5. In Vitro Tests Performed with Modified Surfaces.

A. Radio-labeled biocompatible agents.

Radiolabeled [³H] biocompatible agents were photolabeled as described above and photocoupled to plastic surfaces. The plastics surfaces were extensively washed with PBS, then dissolved in organic

solvent, and counted by liquid scintillation spectrometry. Some representative results are given in the Table 2.

Table 2. Sample results of amounts of growth factors photocoupled to various materials

<u>Photolabeled Biocompatible Agent</u>	<u>Solid Surface</u>	<u>Ng Growth Factor Applied/cm²</u>	<u>Ng Growth Factor Photocoupled/cm²</u>	<u>% Coupling Efficiency</u>
ANP-EAC-FN	PVC	843.04	677.6	80.4%
	Polyurethane	843.04	823.04	97.6%
BBA-FN	PVC	3564.0	1091.2	30.62%
	Polyurethane	3564.0	2622.4	73.58%
ANP-EAC-COL	PVC	2675.2	374	14.0%
	Polyurethane	2675.2	2173.6	81.26%
BBA-COL	PVC	1105.2	197.56	17.9%
	Polyurethane	1105.2	920.3	83.3%

As these results show the photolabeled biocompatible agents covalently coupled to these surfaces.

B. Attachment of Bovine Endothelial Cells to Modified Plastic Surfaces. Bovine endothelial cells were collected from fetal animals 8-24" in length. Cornea, aorta and umbilical endothelial cells were harvested aseptically. Cells were grown in a 5% CO₂ incubator at 37°C in a known high glucose cell growth medium such as Dulbecco's modified Eagle's medium (described in R. Dulbecco and G. Freeman, Virology, Vol. 8:396 (1959) and J. D. Smith, G. Freeman, M. Vogt and R. Dulbecco, Virology, Vol. 12:185-196 (1960)) with 25mmole HEPES buffer, 10% bovine calf serum, and 2.5 micrograms amphotericin B/ml (the "growth media"). Once the plates, tubes or sheets were prepared; cell cultures were prepared from primary cell lines. The cells were detached from the

cell lines with a 0.25% solution of trypsin and resuspended in the growth media. Cells were then counted using a trypan blue (0.4%) solution and a hemocytometer. Various concentrations of cells were layered on the prepared materials. Cell attachment was monitored for various time periods from 5 minutes to 14 days. Attachments were determined by at least two methods. In one, sample materials were removed from culture media and washed 2 times with sterile saline. Cell stains were then applied and total cells on the surface were counted. A second method was to trypsinize the cells off the surface with a trypsin solution and count using the trypan blue method.

Representative results of the attachment and outgrowth of endothelial cells on precoated polyvinyl chloride plastic pieces are reported in Table 3. The number of viable cells attached to each piece were determined by trypan blue staining procedures.

Table 3. Cell attachment determinations and outgrowth of endothelial cells on the treated polyvinyl chloride surface.

Biocompatible agent and chemical-linking moiety	Ng growth factor/cm ²	3-day cell counts*	7-day cell counts	7-day outgrowth*
ANP-EAC-FN	677.6	2610(2+-3+)	3539(2+-3+)	1.5-1.75mm(2+)
BBA-FN	1091.2	868(1+-2+)	14500(2+)	3.75-4.25mm(2+-3+)
ANP-EAC-COL	374.0	14500(3+-4+)	15833(2+-3+)	1.0-3.0mm(3+)
BBA-COL	197.6	5749(2+)	21500(3+)	2.5-4.0mm(3+)
Control PVC		0	7(2+)	1.5-2.0mm(3+)

C. Attachment of Human Umbilical Endothelial Cells. Primary human endothelial cells were harvested

- 20 -

from fresh (less than 4 days old) human umbilical cords. Cords were rinsed with 20 mls-cord buffer (0.144M NaCl, 0.004M KCl and 0.001M PO_4) twice to remove blood and clots. Collagenase was pushed into the cord and left for 20 minutes at room temperature. Using 10 ml of warm cord buffer, the collagenase and detached cells were flushed into tubes. The suspension in the tubes were combined and centrifuged at 1500 rpm for 5-10 minutes. The supernatant was poured off and the cells resuspended in 10 ml of cord buffer. Following the second centrifugation, the cells were resuspended in cord buffer and plated into tissue culture disks. All cells were incubated in 37°C incubator with 5% CO_2 . Cells were radiolabeled using ^{51}Cr in cord media without calf serum.

Labeled cells were then used for cell attachment studies. Plates, sheets, and tubes of the plastics described above were prepared as recorded above. The cells were trypsinized and counted with the trypan blue method. Cells were allowed to adhere to the prepared plastic for three hours to seven days. Cells were rinsed off and the total number of any results attached cells were compared to the number of non-attached cells. Representative results appear in Table 3 above.

D. Outgrowth Measurement using Endothelial Cells. The following techniques were used to monitor the outgrowth of cells from a point of origin as the cells grow to cover the surfaces of the plastics listed above modified as follows. Solutions of biocompatible agents containing from 0 to 500 micrograms of cell factors were coated onto surfaces from 1

- 21 -

to 6 cm long to establish a gradient. Cells were not detached from the tissue with trypsin or any proteinase. The tissue was placed on a point of origin at the low end of the gradient and marked. The tissue was allowed to sit for 15 minutes at room temperature. Growth media was added to give a moist coating over the plastic. All protocols were carried out using aseptic conditions. Plates were then incubated at 37°C in a 5% CO₂ incubator. Outgrowth was measured daily for up to two weeks or until the length of plastic was completely covered. Outgrowth on the treated surfaces was compared to nontreated control surfaces as reported in Table 3 above. All materials were rinsed and stained for permanent scanning electron microscopy.

These results demonstrated that the covalent attachment of the growth factors fibronectin (FN) and collagen (COL) to the plastic surface improved the biocompatibility of the plastic with bovine endothelial cells. The cells preferentially attached to the modified surfaces versus control surfaces as is indicated by the distance they grew out over the plastic surface.

6. In Vivo Studies.

Two conditioned dogs were obtained for this study. Pieces of GORE-TEX (reinforced expanded polytetrafluoroethylene, a trademarked product of W. L. Gore and Associates, Inc.) were precoated with FN, ANP-EAC-FN (adsorbed and photocoupled), ANP-EAC-FN (adsorbed only) and a PBS-control. The testing was a blind study. The grafts were labeled by lettering; however, the surgical team did not know which grafts had modified surfaces and which were controls. Each dog received two 6mm x 5cm pieces of GORE-TEX implanted in the left and right iliac artery. The

- 22 -

grafts were left in the dogs for one month (30 days). The dogs were given the anti-inflammatory drugs Persontine and Aspirin to mimic human implant procedures.

Both control grafts (PBS and FN) were patent and had sufficient caliber. The anastomatic lines were intact and the inner surfaces were smooth. Endothelialization was incomplete with the control grafts. There appeared to be no evidence of significant thrombosis. Both grafts to which ANP-EAC-FN was bound (photocoupled and adsorbed only) were free of thrombosis formation. Endothelialization was complete giving the inner surfaces of the grafts a smooth, shiny appearance.

Example 2

Modification of the Surfaces of Contact Lenses and Introcular Lens Implants

The experiments described in this example involved preparations of hydrophilic polymers (a biocompatible agent) bound to a chemical linking moiety, photocoupling the moieties to contact lens surfaces, and measuring the in vitro protein deposition from artificial tear solutions onto these lenses in comparison to non-treated lenses. Experiments to study the compatibility of the biocompatible agents in vitro with corneal pieces and in vivo in rabbit eyes were conducted to assure that there were not toxic or irritant reactions to the resulting lenses.

1. Binding Biocompatible Agents to the Chemical Linking Moiety.

A. Preparation of Photolabeled Polyethylene Glycols. Polyethylene glycols of molecular weights 1000 (PEG-1000) and 4000 (PEG-4000) were labeled with fluoronitroazidobenzene (FNAB) by modification of the phase transfer method of "Kimura,

and S. Regen, Journal of Organic Chemistry 48; 195 (1983) the teachings of which are incorporated by reference herein. Briefly, the phase-transfer synthesis of 4-azido-2-nitrophenyl polyethylene glycol (ANP-PEG) involved the mixture of 60% aqueous potassium hydroxide ("KOH")/toluene with FNAB and PEG, followed by extraction and thin layer chromatographic (TLC) purification as described below.

ANP-PEG-1000. ANP-PEG-1000 was prepared by adding 0.05 mmole PEG-1000 to 5 mls 60% KOH and 0.5 mmole FNAB to 10 ml toluene. This reaction mixture was rapidly stirred at room temperature for 16 hours. The product was isolated from the organic layer. TLC in 85/15/1/1 chloroform/methanol/H₂O/acetic acid or ammonium hydroxide separated mono- and di-substituted derivatives of ANP-PEG-1000 from unlabeled PEG. The band corresponding to ANP-PEG-1000 (lower R_f value) was extracted from silica gel with TLC solvent and azeotrophed to remove residual acid or base. The final product was soluble in water and resulted in the conversion of 30-40% of the PEG starting material to ANP-PEG-OH product.

ANP-PEG-4000. The ANP-PEG-4000 was prepared by the same procedure as that described above except that the reaction mixture was rapidly stirred at 50°C to ensure all reagents remained in solution during the course of the reaction. The yield of ANP-PEG-4000-OH was 10%.

B. Preparation of Photolabeled Jeffamines. Polyoxypropylenepolyamines and polyoxyethylenepolyamines (referred to as "Jeffamines", a trademark of Jefferson Chemical Co., Inc.)

- 24 -

were photolabeled by coupling the N-oxy succinimide ("NOS") esters of ANP-EACA, BBA and nBBA to the polymers. These NOS-derivatives were added in 0.5X amounts to 1X Jeffamine in very dry (high purity) solvents (ANP-EAC-NOS in dry tetrahydrofuran, BBA-NOS in dry dioxane or dimethylformamide and nitro BBA-NOS in dry dioxane or dimethylformamide). After 16 hours of reaction at room temperature in the dark, the products were isolated by TLC in 85/15/1/1/ chloroform/methanol/H₂O/acetic acid. Monosubstituted Jeffamine derivatives were extracted with the TLC solvent and azeotrophed with water to remove the residual acetic acid. The water-soluble products ANP-EAC-Jeffamine, BBA-Jeffamine, and nBBA-Jeffamine were isolated in 15%, 10% and 12% yields, respectively.

C. Preparation of ANP-Hyaluronic Acid.

The terminal sugar of human placental hyaluronic acid (MW_{app} 100-130,000) was activated by the periodate procedure described in E. Junowicz and S.E. Charm, "The Derivatization of Oxidized Polysaccharides for Protein Immobilization and Affinity Chromatography," Biochimica et Biophysica Acta, Vol. 428: 157-165 (1976) and incorporated herein by reference. This procedure entailed adding sodium or potassium periodate to a solution of hyaluronic acid thus activating the terminal sugar. The hyaluronic acid was added to a 10-fold excess of Jeffamine and allowed to react 4 hours at room temperature. The linkages were stabilized by reduction with sodium cyanoborohydride, followed by exhaustive dialysis to remove most of the excess Jeffamine. A 10-fold molar excess of ANP-EAC-NOS in DMF was added to the Jeffamine-hyaluronate in 0.1 M carbonate, pH 9.0, by syringe

- 25 -

drive. This addition required 16 hours and was conducted at room temperature in the dark. The excess ANP-EAC-NOS and ANP-EAC-Jeffamine was removed by gel filtration chromatography. The integrity of the azide group, which is required for photocoupling of the moiety to the contact lens polymer backbone, was analyzed by infrared spectroscopy to detect the ANP group, a polyethylene glycol assay to detect the Jeffamine spacer, and a modified carbazole assay described in T. Bitter and H. Muir, Analytical Biochemistry Vol. 4: 330-334 (1962) and incorporated herein by reference to determine the uronic acid content of the derivative.

The polyethylene glycol assay was developed using the Dragendorff reagent (tetraiodobismuthic acid-barium chloride). A 5-ml portion of stock reagent (425-mg bismuth nitrate, 10-gm potassium iodide in acetic acid and water) was added to 10-ml 10% barium chloride in water and a background reading at 516-nm was noted. Then 0.1-ml of the sample was added and the contents mixed by inversion of the cuvette. A reading was taken at 516-nm after 1 minute of incubation. The values were compared to a standard curve.

The carbazole assay was performed as follows. A 3.0 ml portion of sulfuric acid reagent (0.025M sodium tetraborate-10 H₂O in sulfuric acid) was cooled to -70°C. A 0.5 ml portion of sample was layered onto the acid and the mixture was stirred (30 min.) until it reached room temperature. The tubes were heated at 100°C. (10 min.), a 0.1 ml aliquot of carbazole reagent (0.125% carbazole in absolute ethanol) was added, the tube contents were mixed (5 min.), heated at 100°C. (15 min.), then cooled to room

- 26 -

temperature in an ice bath. The samples were analyzed spectrophotometrically at 530 nm against a sulfuric acid reagent blank. The results were compared to a standard curve constructed with 4-40 ug/ml glucuronolactone standards. The assay was sensitive to detecting 20 pmole of hyaluronic acid.

The fractions containing one ANP, one Jeffamine and one hyaluronate molecule were pooled and used as a biocompatible agent.

D. Preparation of Photolabeled Hyaluronic Acid, Methyl Cellulose and Chondroitin Sulfate.

ANP-EAC-Jeffamine, BBA-Jeffamine and nitro-BBA-Jeffamine were linked to the carboxyl groups of uronic acid residues of hyaluronic acid and chondroitin sulfate by a carbodiimide procedure as follows. A 5 molar excess of photolabeled Jeffamine and 1-ethyl-3-(3-dimethylaminopropyl) carbodiimide with HCl was mixed with the polysaccharide polymer in water adjusted to pH 4.5 with 0.1N HCl. The mixture was allowed to react at room temperature in the dark for 24 hours. The product was purified by gel filtration chromatography then analyzed for photogroup and carbohydrate content as described above.

E. Preparation of Photolabeled Collagen.
Human placenta Type IV collagen (available from Sigma Pharmacueticals) was dissolved at a 1 mg/ml concentration in 0.1M borate, pH 9.0. ANP-EAC-NOS in DMF, BBA-sulfa-NOS in dioxane or nitro BBA-NOS in dioxane was slowly added to the collagen solution in a 50x molar excess by syringe drive at 4°C in the dark over 16 hours. After the addition was complete, the mixture was stirred 4 hours in the cold. The collagen product was dialyzed against 4 changes of PBS then centrifuged to remove insoluble material. The

supernatant was measured spectrophotometrically at 260 nm, 280 nm and 462 nm to assess the photogroup/protein ratio.

F. Preparation of Photolabeled Proteins. ANP-EAC-NOS, BBA-NOS and nBBA-NOS photogroup dissolved in organic solvent at 25 mg/ml concentrations, were added in 50 molar excess to papain (papaya, MW 23,426) by syringe drive at 4°C in the dark over 16 hours. After addition of the photogroup was completed, the mixture was stirred an additional 4 hours, then dialyzed in PDS to remove uncoupled photogroups. After dialysis, the product was centrifuged to remove insoluble material. The supernatant was measured spectrophotometrically at 260 nm, 280 nm, and 462 nm to estimate the photogroup/protein ratio.

2. Photocoupling Biocompatible Agents to Lens Surfaces. The photolabeled biocompatible agents obtained above were added to the contact lens materials described in Table 4 at a concentration of 250-1000 pmole agent/contact lens. The solution was allowed to adsorb onto the contact lenses at room temperature in the dark for 3 hours. The photolabeled agents were then covalently linked to the plastic by photolysis for 12 hours at the appropriate wave length (450 nm for ANP and 320 nm for BBA and nBBA derivatives). After photolysis, the contact lenses were washed with 5x5 ml of normal saline (0.85% NaCl) to remove non-covalently linked groups.

Radiolabeled groups may be coupled to the lens materials, and the lens pieces treated with tetrahydrofuran followed by DMSO to release the radiolabel from the solid surface. Scintillation fluor is then added and the amount of biocompatible agent/cm²

determined by liquid scintillation spectroscopy.

Representative results are shown in Table 4.

Table 4. Load Densities of Biocompatible Agents on Various Contact Lens Materials

Biocompatible Agent	Contact Lens Material	*pmole/cm ²	ng/cm ²	Coupling Efficiency
ANP-1000	Polyvinyl chloride	19.96	19.96	22.86%
	Sofspin (polymacon)	33.45	33.45	12.95%
	Permaflex	33.97	33.97	12.90%
	Vistamarc	34.26	34.26	13.20%
	Lidofilcon	63.12	63.12	24.30%
	Silicone	33.97	33.97	4.80%
	**Polymacon Button	2408.60	2408.60	38.23%
ANP-4000	Sofspin (polymacon)	27.06	108.24	10.50%
	Permaflex	42.86	171.44	16.50%
	Silicone	170.60	682.40	22.70%
	**Polymacon Buttons	1574.00	6296.00	25.00%
nitro BBA-2000	Polyvinyl Chloride	23.20	46.40	26.60%
	Sofspin	13.14	26.28	5.10%
	Permaflex	8.21	16.42	3.20%
	Silicone	95.61	191.22	13.50%
	**Polymacon Buttons	3738.00	7476.00	56.45%
BBA-2000	Silicone	113.20	226.40	15.60%
	**Polymacon Buttons	4035.10	8070.20	64.30%
ANP-Hyal-uronic acid	Silicone	25.00	25.00	7.00%
	**Polymacon Buttons	130.95	130.95	7.90%

* Values were averaged from replicates of 10

** Polymacon loads are based on total volume, cm³, rather than surface area.

Sofspin contacts are made of polymacon (polymethacrylate) with about 38.6% water and are a trademarked product of Bausch & Lomb, Inc.

Permaflex contacts are made of polymethacrylate with about 74% water and are a trademarked product of Coopervision, Inc.

Vistamarc contacts are made of polymethacrylate with about 58% water and are a trademarked product of Johnson & Johnson.

- 29 -

Lidofilcon contacts are made of polymethacrylate with about 70% water and are a product of Bausch & Lomb, Inc.

The values in Table 4 are expressed as pmole biocompatible agent per square centimeter surface area or ng/cm^2 .

The coupling efficiencies were based upon addition of 260 pmole/cm^2 biocompatible agent/contact lens materials, 710 pmole/cm^2 biocompatible agent/silicone, and 660 pmole/cm^3 biocompatible agent/ cm^3 polymacon button. ANP-hyaluronate was added at 357 pmole/cm^2 to silicone and at 1655 pmole/cm^3 to polymacon button material. The ANP derivatives coupled at higher load densities than the nBBA-Jeff on the hydrogel contact lens materials. These results were reversed for the silicone compound.

3. In Vitro Protein Adsorption Studies. Artificial human tears were prepared according to the formula found in B.P. Gloor, "The Lacrimal Apparatus" in Adler's Physiology of the Eye: Clinical Applications (R.A. Moses, ed.), C.V. Mosby Co., St. Louis, MO (1981) the teachings of which are incorporated herein. As indicated in that reference the major proteins present in human tears are serum albumin (HSA), gamma-globulin (HGG), and lysozyme (LYZ). The major sterols present in human tears are cholesterol and cholesterol esters.

A. ^3H Proteins. The protein components were tritiated by reductive methylation with formaldehyde and tritiated sodium borohydride as described in N. Jentoft and D. C. Dearborn, Journal of Biochemistry, Vol. 254: 4359-4365 (1979) and incorporated herein by reference. Briefly, the biocompatible agent in 1mg/ml concentration in 0.1M HEPES,

- 30 -

pH 7.4 was methylated by formaldehyde reacting with tritiated sodium borohydride and rocking at 22°C for about 2 hours. The product was dialyzed against PBS in 0.01M phosphate, 0.15M sodium chloride, pH 7.4, and affinity purified on gelatin sepharose. Bound agent was eluted with 1M sodium bromide 0.02M sodium acetate, pH 5.0 then dialyzed against PBS, pH 7.4.

B. Preparation of Artificial Tears. The radiolabeled proteins described above were used in preparation of artificial tears. One of the radiolabeled proteins or the tritiated cholesterol was included in each tear mixture. The other components were not radiolabeled. The contact lens materials were incubated in the artificial tear solution for one week at 37°C with gentle agitation. At the end of this time the lens materials were washed with 5 x 10ml of 0.85% NaCl. The amount of protein adsorbed to the lens materials was then determined by liquid scintillation counting.

In vitro protein deposition results are given in Table 5. Reduction in total protein deposition reached 85% in ANP-1000-OH modified Sofspin lenses. Individual biocompatible agents increased or stayed at the same levels as some of the control contact lens materials, but the overall protein amounts were reduced for all lens materials except ANP-1000-OH coated Polymacon buttons, ANP-4000-OH coated polymacon buttons and ANP-hyaluronate coated polymacon buttons. These poor results were all obtained with virgin polymacon materials which appears to react differently than polymacon contact lenses, such as Sofspin lenses. Overall, these in vitro protein deposition studies demonstrated significant to dramatic decreases in protein deposition from artificial tears on various contact lens materials during a one week period.

Table 5: In Vitro Proteins Adsorption from Artificial Tears: ^3H Proteins*

Biocompatible Agent	Contact Material	ugHSA/ cm ²	% of control	ugHgg/ cm ²	% of control	% of ugHys/ cm ²	% of control	ug Total Protein	% of control	% Reduction Total Protein
Controls	Polyvinyl Chloride	.525	100.00	.524	.441		1.49			
	Sofspin					.576		3.162		
	(Polymacon)	1.256		1.33						
	Permaflec	.978		1.953	1.866		4.797			
	Vistamarc	.553		.343	47.86		48.76			
	Lidofilcon	2.154		1.009	1.423		4.586			
ANP-1000-OH	Silicone	1.121		.272	.264		1.657			
	**Polymacon Buttons	32.23		6.983	2.46		41.673			
	Polyvinyl Chloride	.298	56.8	.696	133	.0384	8.7	1.032	69.3	30.7
	Sofspin	.241	19.2	.191	14.4	.04	6.9	.472	14.93	85.07
	Permaflec	.582	59.5	1.351	69.2	1.693	90.73	3.626	75.6	24.4
	Vistamarc	.187	33.8	.378	110.2	39.19	81.88	39.76	81.5	18.5
ANP-4000	Lidofilcon	.640	29.7	.440	43.6	1.73	121.5	2.81	61.3	38.8
	Silicone	.103	9.2	1.016	373.5	.214	81.1	1.333	80.4	19.6
	**Polymacon Buttons	36.00	111.0	5.44	77.9	2.47	100.0	43.91	105.4	(-5.4)
	Polyvinyl Chloride	.430	81.9	.356	67.9	.148	33.6	.934	62.7	37.3
	Sofspin	1.16	92.4	.608	45.7	.297	51.6	2.065	65.3	34.7
	Vistamarc	.187	33.8	.686	200.0	43.24	90.3	44.11	90.5	9.5
ANP-4000	Silicone	1.082	96.5	.242	88.9	.210	79.5	1.534	92.6	7.4
	**Polymacon Buttons	37.62	116.7	4.172	59.7	1.863	75.7	43.655	104.7	(4.7)

Biocompatible Agent	Contact Material	ugHSA/ cm ²	% of control	ugHSA/ cm ²	% of control	ugLys/ cm ²	% of control	ug Total Protein	% of control	% Reduction Total Protein
nBBA-Jeff	Polyvinyl Chloride	.632	120.3	.576	109.9	.072	16.33	1.28	85.9	14.1
	Sofspin	.665	52.9	.859	64.5	.531	.922	2.055	64.9	35.1
	Silicone	.978	87.2	.061	22.4	.068	25.8	1.107	66.8	33.2
	**Polymacon Buttons	26.35	81.76	.01	.14	.01	.41	26.37	63.28	36.72
BBA-Jeff	Polyvinyl Chloride	.326	62.1	.454	86.6	.290	66.7	1.07	71.8	28.2
	Silicone	.921	82.15	.089	32.7	.149	56.4	1.159	69.9	30.1
	**Polymacon Buttons	30.61	94.9	3.695	52.9	.01	.40	34.32	82.34	17.66
ANP-Jeff	Polyvinyl Chloride	.486	92.6	.456	87.0	.192	43.5	1.134	76.1	23.9
	Silicone	.904	80.6	.231	83.7	.257	97.6	1.392	84.01	15.99
	**Polymacon Buttons	35.48	110.1	5.62	80.5	1.94	78.86	43.04	103.3	(3.3)

* The values are calculated from 10 replicates

** Polymacon buttons are based on volume rather than surface area cm³

*** Values in parentheses indicate an increase in protein adsorption

The results of the in vitro cholesterol deposition studies are given in Table 6. The amount of cholesterol deposition after 7 days of incubation in artificial tears was reduced by as much as 83% on polyvinyl chloride. All contact lens types exhibited reduction of cholesterol deposition except the polymacon button pieces. Again, these materials react differently than the contact lenses made of the same polymer.

Table 6: Cholesterol Adsorption from Artificial Tears:
³H Cholesterol

<u>Biocompatible Agent</u>	<u>Contact Material</u>	<u>*ug Cholesterol/ cm²</u>	<u>% of Control</u>	<u>% Reduction</u>
Controls	Polyvinyl Chloride	.096	100	72.9
	Sofspin	.091	100	
	Permaflex	.196	100	
	Vistamarc	.032	100	
	Lidofilcon	.053	100	
	Silicone	.103	100	
	Polymacon Button	.215	100	
ANP-1000	Polyvinyl Chloride	.026	27.1	72.9
	Sofspin	.075	82.4	17.6
	Permaflex	.134	68.4	31.6
	Vistamarc	.028	87.5	12.5
	Lidofilcon	.046	86.8	13.21
	Silicone	.086	83.5	16.5
	Polymacon Button	.245	113.9	** (13.9)
ANP-4000	Polyvinyl Chloride	.0166	17.3	82.7
	Sofspin	.101	110.9	(10.9)
	Permaflex	.134	68.4	31.6
	Vistamarc	.023	71.9	28.1
	Silicone	.104	100.9	(0.9)
	Polymacon Button	.248	115.3	(15.3)
nBBA-Jeff	Polyvinyl Chloride	.038	39.6	60.4
	Sofspin	.138	151.6	(51.6)
	Permaflex	.164	83.7	16.33
	Silicone	.072	69.9	30.1
	Polymacon Button	.148	68.8	31.2
BBA-Jeff	Polyvinyl Chloride	.0214	22.3	77.7
	Silicone	.107	103.8	(3.8)
	Polymacon Button	.230	106.9	(6.9)
ANP-Jeff	Polyvinyl Chloride	.028	29.2	70.2
ANP-Hyaluronate	Silicone	.224	217.5	(117.5)
	Polymacon Button	.238	110.6	(10.6)

* Values were the averages of ten replicates.

** Values in parentheses indicate increase in cholesterol adsorption.

C. Amino Acid Analysis. Control and surface modified lenses were incubated in the artificial tear solution for one week at 37°C with gentle agitation. The lenses were washed with 5 10ml washes of 0.85% NaCl, then hydrolyzed with 6N HCl and the hydrolysates subjected to standard amino acid analyses on an amino acid analyzer. Total amino acid content of control and surface modified lenses were compared to each other. Reduction in total amino acid content indicated a reduction in protein absorption.

The total amino acid analyses of the acid hydrolyzed contact lenses are given in Table 8. These results are expressed as total amino acids in nmole/ml. These results again indicated that the ANP-1000-OH, ANP-4000-OH and nBBA-Jeff modifications of Sofspin polymacon lenses reduced the deposition of proteins on the lenses after 7 days of incubation in artificial human tears.

Table 7: Total Amino Acid Analyses from Artificial Tear Deposits on Contact Lenses

Contact Material	Biocompatible Agent	Total Amino Acids nmol/lens no NH ₃	% Reduction
Sofspin	ANP-1000	62.75	59.7
	ANP-4000	136.272	12.4
	nBBA-Jeff	105.381	32.3
	Control	155.616	----
Permalens	ANP-1000	168.714	32.5
	ANP-4000	210.207	15.9
	nBBA-Jeff	181.302	27.5
	Control	249.939	----

4. In Vitro Toxicity Testing. The biocompatible lens materials described above were tested for irritant or toxicity responses. Control and biocompatible lenses were prepared under sterile conditions with final washing procedures conducted in a laminar flow hood. The lenses were placed in a solution of a

- 36 -

known high glucose cell medium such as Dulbecco's Modified Essential Medium, with 10% fetal calf serum, and 5% glutamine (to which antibiotic and anti-fungal agents had been added). Pieces of viable 3-5 month fetal bovine corneas were placed on top of the lenses. The epithelial surface of the cornea was placed in contact with the lens surface in some studies, and the endothelial cell surface was placed directly on the lens surface in other studies. The systems were placed in culture at 7-10% CO₂ and 37°C for 1-2 week periods. At various intervals after initiation of culture the viabilities of the epithelial and/or endothelial cells were assessed by staining procedures.

5. In Vitro Assay for Stability of Covalent Bond. The stability of the covalent attachment was assessed by subjecting the surface-modified polymacon (polymethacrylate) to enzymatic cleaner (papain), thermal disinfection and chemical disinfection (buffered aqueous solution containing sodium chloride, sodium-borate and boric acid.) These results are given in Table 8.

Table 8: Stability of Covalent Linkage to Cleaning Disinfection Procedures

<u>Biocompatible Agent</u>	<u>Treatment</u>	<u>pmole/cm3</u>	<u>% Remaining</u>
ANP-1000	No treatment	831	100
	Enzymatic cleaner	862	100
	Boiling	761	91.6
	Chemical cleaner	721	86.8
ANP-4000	No treatment	1574	100
	Enzymatic cleaner	2012	100
	Boiling	2092	100
	Chemical cleaner	1564	99.4
nBBA-2000	No treatment	1732	100
	Enzymatic cleaner	1785	100
	Boiling	1795	100
	Chemical cleaner	1129	65.2
BBA-2000	No treatment	1651	100
	Enzymatic cleaner	1996	100
	Boiling	1619	98.1
	Chemical cleaner	1409	85.3
ANP-Hyaluronate	No treatment	300	100
	Enzymatic cleaner	317	100
	Boiling	340	100
	Chemical Cleaner	307	100

* Values are the averages of 10 replicates

The covalent linkages remained 100% stable to enzymatic cleaning and thermal disinfection. There was some loss of biocompatible agent with the chemical disinfection procedures except for the ANP-hyaluronate.

6. In Vivo Assessment of Biocompatibility. Preliminary in vivo biocompatibility testing was conducted in rabbit model systems. A population of at least 24 animals was used in each study. Scleral lenses designed to fit rabbit eyes were used in these studies. The rabbits wore lenses according to the following schedule:

6 rabbits	No lens left eye, control lens right eye
6 rabbits	Control lens left eye; physically treated lens (same physical treatment as surface modified lenses but not coated with biocompatible agent) right eye
12 rabbits	Control lens left eye; surface-modified lens right eye.

The rabbits were anesthetized with Ketamine/Xylazine prior to placing the lenses in the rabbit eyes. A methyl cellulose/normal saline wetting solution was applied hourly to maintain adequate eye and lens lubrication. The contacts were worn 8 hours/day. After chosen periods of lens wear the rabbits were analyzed by slit lamp and fluorescein dye methods. The degree of eye irritation was graded by the McDonald-Shadduck scale as described in T.O. McDonald and J.A. Shadduck, "Eye Irritation," in Advances in Modern Toxicology, Vol. 4, pp. 162-166 (1977) incorporated herein by reference. The McDonald-Shadduck procedure allows the investigator to grade conjunctival

congestion, conjunctival swelling, conjunctival discharge, aqueous flare, iris involvement and corneal cloudiness and other characters on a scale of 0-4, with 0 being normal and +4 the most complete involvement.

The results of the in vivo rabbit studies are given in Table 9. The McDonald-Shadduck scores for the rabbits are represented in the table. Mann-Whitney U tests were performed on these results and indicated that there were no statistical differences between the surface-modified and control lenses ($p < 0.05$). Therefore, these tests indicate that in this 4-day study in rabbits, no detectable differences in conjunctival congestion, conjunctival swelling, conjunctival discharge, aqueous flare, iris involvement, corneal cloudiness, pannus vascularization, norepithelial damage of the surface modified lenses was detected as compared to control lenses. The irritation which was demonstrated in the control and the modified lenses appeared to be associated with the rabbits' development of tolerance to contact lenses.

Table 9: Average McDonald-Shadduck Scores
For In Vivo Rabbit Study

	Day 1	Day 2	Day 3	Day 4
Control Lens	0.53	0.78	0.19	0.33
Surface Modified Lens	0.58	0.65	0.17	0.21

Example 3

Coupling of Albumin, Heparin and Urokinase to Polyurethane Tubing

1. Preparation of Photolabeled Albumin. Serum albumin (canine) was dissolved in 0.1M borate buffer at pH 9.0. A volume of 4-azido-2-nitrophenyl-6-aminocaproyl-N-oxysuccinimide (ANP-EAC-NOS) solution

at 25 mg/ml in DMF to provide a 10 fold molar excess of ANP-EAC-NOS over albumin was added to the albumin with stirring at room temperature in the dark over about 12 hours using a syringe drive. The solution was then dialyzed in the dark against three one liter volumes of phosphate buffered saline (PBS). After dialysis, the solution was centrifuged to remove insoluble material. The absorbance at 470 nm of a 1/100 dilution was measured spectrophotometrically to estimate the ANP/albumin ratio.

2. Photocoupling of Albumin to Polyurethane Tubing.

Polyurethane tubing was dipped into dioxane for thirty seconds after which it was immediately rinsed with deionized water. The etched tubing was immersed in a solution of photoreactive albumin for at least two hours at room temperature in the dark with mixing. The tubing was then air dried for at least ten minutes in the dark, then exposed to high intensity visible light for at least one hour. The immersion in photoreactive albumin, drying and photolyzing was repeated twice, the last time the dipping was left overnight. The tubing was then washed in 1.0 N NaCl for one hour at room temperature. The NaCl solution was changed at least once during the one hour.

3. Coupling of Heparin to Albumin on Polyurethane Tubing. The albumin-polyurethane tubing was immersed in 5.0 ml. of deionized water. 200 mg of 1-ethyl-3-(3-dimethylaminopropyl) carbodimide (EDC) was dissolved in the water, then the pH was adjusted to 4.0 with 1N HCl. One ml of water containing 30 mg of heparin was added to the EDC solution. The pH was again adjusted to 4.0 with 1N HCl. The solution containing the immersed polyurethane tubing was mixed for two hours at room temperature after which another 200 mg of EDC was added. The reaction was then allowed to

continue overnight at room temperature. The tubing was then rinsed in PBS to remove uncoupled heparin and reaction biproducts.

4. Coupling of Urokinase to Albumin on Polyurethane Tubing. Polyurethane tubing having serum albumin immobilized thereon was immersed in 1.25% glutaraldehyde in 0.1M phosphate buffer, pH 7.0 for 15-18 hours at room temperature. The tubing was then washed in deionized water for 30 minutes, the water being changed at least once during that time. The polyurethane-albumin-glutaraldehyde was then immersed in a solution of urokinase (8.3 units/ml, 2-3 mg/ml) in 0.1M borate of pH 9.0 and mixed overnight at 4°C. The tubing was then rinsed for four hours in PBS after which it was assayed for urokinase activity.

Two polymers were used as the solid surface, polyurethane and polyhema. The modified surfaces yielded 1-10 mg heparin/cm² and 0.6-1.3 mg urokinase/cm².

Example 4

Coupling of a Film to a Solid Surface

Formation of a Coating Film and its Covalent Attachment to a Surface. Preparation of ANP-hyaluronic acid. Photolabeled derivatives of hyaluronic acid (ANP-EAC-Jeffamine, BBA-Jeffamine and nitro-BBA-Jeffamine) were prepared as previously described.

Films are formed from the photoreactive coating material and placed on surfaces of contact lenses (by dipping and drying) in the dark. Covalent attachment to the biomaterial surface and strengthening of the film by intermolecular cross-linking may be accomplished through illumination.

In another example, an artificial hip joint is soaked in ANP-EAC-Jeffamine-hyaluronic acid (.1:1 mg/ml) for three hours in the dark. The joint is then removed from solution and allowed to dry forming a thin film of coating material on the artificial joint. The film is then covalently attached to the joint by illumination at 400 to 450 nm for 8 hrs. at 4°C. The joint is then rinsed in physiological saline to remove uncoupled ANP-EAC-Jeffamine-hyaluronate. The hyaluronic acid bound to the bone reduces friction and reduces wearing of the bone in the joint area.

100 mg of bovine serum albumin is dissolved in 2 ml of .1M borate buffer pH 9. 14mg of ANP-AUD-NOS is dissolved in 50 ul of dimethylformamide (DMF). The ANP-AUD-NOS solution is added to the BSA solution slowly over 15 hrs at room temperature in the dark with good stirring. After an additional 3 to 4 hours of stirring the solution is dialyzed against .1M borate buffer at pH 9 in the dark over 24 hrs. with at least 4 changes of 2 liters each of buffer. The dialyzed ANP-BSA is pipetted onto paraffin films in 100 ul aliquots and dried in the dark. After the films have dried they are overlaid with 100 ug aliquots of 1.25% glutaraldehyde and borate buffer pH 9 and incubated for one hour at room temperature in the dark. The films are then washed by slowly dropping water onto them while still on the paraffin films and allowing the water to run off. After one hour of such washing, the films are redried and then carefully lifted off the paraffin film and transferred to a plastic surface (e.g., polyurethane). On the plastic surface the films are again wetted with water containing 20% dioxane, then redried in the dark. The films on the plastic surfaces are then exposed to high

intensity visible light for four hours at 4°C to bind the film to the surface with a fan blowing across the surface to prevent excessive heating of the surface.

While a preferred embodiment of the present invention has been described, it should be understood that various changes, adaptations and modifications may be made therein without departing from the spirit of the invention and the scope of the appended claims.

CLAIMS

What is claimed is:

1. A method of providing a biomaterial with a desired biocompatible surface, the method employing a solid surface of the biomaterial, molecules of a biocompatible agent, and a chemical linking moiety possessing a photochemically reactive group capable upon activation of covalently bonding to the solid surface, and possessing a different reactive group, capable of binding to the molecules of the biocompatible agent, one of the groups being unresponsive to a stimulus to which the other group responds, the method comprising:

activating one of the groups of the linking moiety to cause it to react; and

activating the other of the reactive groups to covalently bind the linking moiety to the solid surface to provide a sufficient population density of molecules of the biocompatible agent to effectively shield the solid surface and to provide a biocompatible effective surface.

2. The method of claim 1 wherein the different reactive group is a thermochemical group.

3. The method of claim 1 wherein the different reactive group is a photochemical group.

4. The method of claim 1 wherein the solid surface is substantially thermochemically unreactive.

5. A biocompatible device having a solid surface carrying molecules of a biocompatible agent, and a chemical linking moiety residue covalently binding separate molecules of the biocompatible agent to the solid surface, the chemical linking moiety residue including the residue of a photochemically reactive

group covalently bonded to the solid surface, and covalently bonded to molecules of the biocompatible agent, the residue of a different reactive group, one of the groups being unresponsive to a stimulus to which the other active group responds, the individual molecules of the biocompatible agent being bound sufficiently proximate to one another as to cause said molecules to effectively shield the solid surface and to provide a biocompatible effective surface.

6. The device of claim 5 wherein the solid substrate is substantially thermochemically unreactive.

7. The device of claim 5 wherein the biocompatible agent is a cell attachment factor.

8. The device of claim 7 wherein the cell attachment factor is laminin or fibronectin.

9. The device of claim 5 wherein the biocompatible agent is a growth factor.

10. The device of claim 9 wherein the growth factor is endothelial growth factor, epithelial growth factor, osteoblast growth factor, fibroblast growth factor, platelet derived growth factor, neural growth factor, or angiogenin growth factor.

11. The device of claim 5 wherein the biocompatible agent is collagen.

12. The device of claim 5 wherein the biocompatible agent is albumin.

13. The device of claim 5 wherein the solid surface is a polymeric substrate.

14. The device of claim 13 wherein the polymeric substrate is polyurethane, polyvinylpyrrolidone, polyamide, polyamine, poly-tetrafluoroethylene, poly(p-phenyleneterephthalamide), polyvinyl chloride, polypropylene, polyacrylate, polymethacrylate, polyacrylamide, polyimine, polyester, polyethylene, cellulose, or silicone.

15. The device of claim 5 in which said device comprises vascular graft tubing, dialysis tubing or membrane, blood oxygenator tubing or membrane, a blood bag, a catheter, a suture, a soft or hard tissue prosthesis, a synthetic prosthesis, an artificial organ, a contact lens or an intraocular lens.

16. A biocompatible lens having a solid surface, molecules of a biocompatible agent, and a chemical linking moiety residue linking separate molecules of the biocompatible agent to the solid surface, the chemical linking moiety residue including the residue of a photochemically reactive group covalently bonded to the solid surface, and covalently bonded to molecules of the biocompatible agent the residue of a different reactive group, one of the groups being unresponsive to a stimulus to which the other reactive group responds, the individual molecules of the biocompatible agent being sufficiently proximate to one another as to cause said molecules to effectively shield the solid surface and to provide a biocompatible effective surface.

17. The lens of claim 16 wherein the lens is a contact lens and the biocompatible agent is a hydrophilic polymer.

18. The lens of claim 17 wherein the hydrophilic polymer is polyethylene glycol, hyaluronic acid, methyl cellulose, collagen or chondroitin sulfate.

19. The lens of claim 16 wherein the biocompatible agent is a proteinase.

20. The lens of claim 19 wherein the proteinase is papain.

21. A method of providing a biomaterial with a desired biocompatible surface, the method employing a

solid surface of the biomaterial, molecules of a bio-compatible agent joined to one another to form a bio-compatible film, said film carrying a chemical linking moiety having a residue of a reactive group covalently bonded to the film and a photochemically reactive group capable upon activation of covalently bonding to the solid surface, said method comprising: activating the photochemically reactive group to covalently bond the film to the solid surface.

22. A biocompatible device having a solid surface carrying molecules of a biocompatible agent joined to one another to form a biocompatible film, said film carrying a chemical linking moiety binding the film to the solid surface, the chemical linking moiety including the residue of a photochemically reactive group covalently bonded to the solid surface, and covalently bonded to the film of the biocompatible agent the residue of a different reactive group one of the reactive groups being unresponsive to a stimulus to which the other reactive group responds.

23. The device of claim 22 wherein the film is albumin.

INTERNATIONAL SEARCH REPORT

International Application No. PCT/US87/02675

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ³

According to International Patent Classification (IPC) or to both National Classification and IPC

IPC (4): A61F 2/54

U.S. Cl. 623/66

II. FIELDS SEARCHED

Minimum Documentation Searched ⁴

Classification System	Classification Symbols
U.S.	128/Dig. 8 435/176, 180 623/1, 5, 6, 11, 66
	351/160R, 160H 427/2

Documentation Searched other than Minimum Documentation
to the extent that such Documents are Included in the Fields Searched ⁴

III. DOCUMENTS CONSIDERED TO BE RELEVANT ¹⁴

Category ⁵	Citation of Document, ¹⁶ with indication, where appropriate, of the relevant passages ¹⁷	Relevant to Claim No. ¹⁴
X	US, A, 3,959,078 (GUIRE) 25 May 1976 See column 4, lines 47-52.	5, 6, 13-18, 22
X	US, A, 4,451,568 (SCHNEIDER ET AL.) 29 May 1984, see the abstract, column 7, lines 28-45 and column 8, lines 6-15.	5, 6, 13-18, 22
Y	US, A, 4,589,881 (PIERSCHBACHER ET AL.) 20 May 1986, see the abstract, column 3, lines 1-18 and column 10, lines 49-68.	7, 8, 12, 23
Y	US, A, 4,526,909 (URIST) 02 July 1985 See column 1, lines 16-20.	9 and 10
Y	US, A, 3,808,113 (OKAMURA ET AL.) 30 April 1974, see column 2, lines 39-48.	11
Y	US, A, 4,378,435 (TAKAGI ET AL.) 29 March 1983, see column 6, lines 11-44.	7, 8, 12, 23

* Special categories of cited documents: ¹⁸

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

IV. CERTIFICATION

Date of the Actual Completion of the International Search ¹

01 February 1983

International Searching Authority ¹

ISA/US

Date of Mailing of this International Search Report ¹

12 FEB 1988

Signature of Authorized Officer ¹⁹

Paul Prebilic



FURTHER INFORMATION CONTINUED FROM THE SECOND SHEET

VI. ☐ OBSERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE ¹⁰

This international search report has not been established in respect of certain claims under Article 17(2) (a) for the following reasons:

1. ☐ Claim numbers _____ because they relate to subject matter ¹² not required to be searched by this Authority, namely:

2. ☐ Claim numbers _____ because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out ¹³, specifically:

VII. ☒ OBSERVATIONS WHERE UNITY OF INVENTION IS LACKING ¹¹

This International Searching Authority found multiple inventions in this international application as follows:

I. Claims 1-4 and 21, drawn to the method of making the product.

II. Claims 5-20 and 22-23, drawn to the product.

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims of the international application.
2. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims of the international application for which fees were paid, specifically claims:
3. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claim numbers:
4. ☒ As all searchable claims could be searched without effort justifying an additional fee, the International Searching Authority did not invite payment of any additional fee.

Remark on Protest

- ☐ The additional search fees were accompanied by applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.